



PRO GOLD INFIELD MIX COLLEGIATE BLEND

1. Gradation – A minimum of 98% of particles shall pass the 2.00 mm sieve with the highest portion of sand particles in the medium to very fine range. Silt and Clay distribution shall be relatively equal with allowable differences no greater than 10%. The final soil classification based on USDA criteria shall be a “sandy loam – sandy clay loam”. This is a single source material and the blending of different parent materials is not acceptable.
2. The color of the material shall be “Gold” to “Reddish Gold”.
3. For installation of new fields place Pro Gold Infield Mix to a final minimum depth of 3-4 inches over a sub-base that is prepared to acceptable specifications. The final grade should be leveled and sloped according to standard infield construction specifications. Allow for +/- 1 inch for compaction
4. For installation of existing fields, properly scarify the surface of the existing material while incorporating +/- 1 inch of Pro Gold Infield Mix. Continue placement of the remainder of Pro Gold Infield Mix that is to be installed.
5. After leveling the infield skin thoroughly water the entire infield surface until the complete depth of the infield mix is moistened. After a period of +/- 4 hours compact with a minimum 2000 lb. static drum roller. If low areas are present, scarify and level low areas with additional Pro Gold Infield Mix.
6. Supplier – Gail Materials (951) 667-6106, www.gailmaterials.net

GAIL MATERIALS

10060 Dawson Canyon Road, Corona, CA 92883
(951) 667-6106 • Fax (951) 667-6102

www.gailmaterials.net